

Shahabad Maroon

Shahabad limestone, Kalaburagi belt, north Karnataka

Deep muted purple-brown from a narrow horizon. Limited output, sold against named projects.

TECHNICAL SPECIFICATION

Compressive strength	132 MPa	BS EN 1926
Flexural strength	18.9 MPa	BS EN 12372
Water absorption	0.28 %	BS EN 13755
Apparent density	2,704 kg/m3	BS EN 1936
Abrasion resistance	16 mm groove	BS EN 14157
Slip, honed	44 dry / 33 wet PTV	BS 7976-2
Slip, brushed	56 dry / 45 wet PTV	BS 7976-2
Frost resistance	48 cycles, no change	BS EN 12371

SIZES, CALIBRATED

600x300, 600x600, 900x600 mm; cut to size to 1800x900 mm

THICKNESSES

18, 20, 25, 30 mm

TOLERANCES

Calibrated finishes +/- 1 mm on thickness, length and width. Riven +/- 3 mm on thickness. Flatness +/- 0.8 mm over 600 mm. Squareness +/- 1 mm on the diagonal.

PACKING

26 m2 per crate at 20 mm; 12 crates per 20 ft; 312 m2 per 20 ft; 1,490 kg gross per crate. Heat-treated ISPM 15 timber crates, 1180 x 820 mm footprint, faces separated with 2 mm closed-cell foam, EPS corner blocks, two-direction 19 mm steel banding.

SUPPLY

Trade supply by the container. Quotations to your nearest port or delivered to your yard, on request. Production 21 to 28 days, 24 to 32 days on the water. Batch test certificates issued with each shipment.

Mallikarjuna Stones Ltd, company no. 17314931, Suite 4 Cutlers Wharf, 18 Effingham Road, Sheffield S4 7YR. +44 114 496 0182, trade@mallikarjunastones.co.uk. Quarry and polishing yard: Mallikarjun Stone Polishing Industries, Survey No. 118/2 Hitnal Road, Miriyan Village, Chincholi Taluk, Kalaburagi District, Karnataka 585307.