

Shahabad Yellow

Shahabad limestone, Kalaburagi belt, north Karnataka

Warm golden buff with visible movement. Deepens markedly when wet. The character stone.

TECHNICAL SPECIFICATION

Compressive strength	108 MPa	BS EN 1926
Flexural strength	15.1 MPa	BS EN 12372
Water absorption	0.46 %	BS EN 13755
Apparent density	2,614 kg/m3	BS EN 1936
Abrasion resistance	20 mm groove	BS EN 14157
Slip, honed	40 dry / 34 wet PTV	BS 7976-2
Slip, riven	66 dry / 57 wet PTV	BS 7976-2
Frost resistance	48 cycles, no change	BS EN 12371

SIZES, CALIBRATED

600x300, 600x600, 900x600, 1200x600 mm; cut to size to 2400x1200 mm

THICKNESSES

20, 25, 30, 40 mm

TOLERANCES

Calibrated finishes +/- 1 mm on thickness, length and width. Riven +/- 3 mm on thickness. Flatness +/- 0.8 mm over 600 mm. Squareness +/- 1 mm on the diagonal.

PACKING

22 m2 per crate at 25 mm; 12 crates per 20 ft; 264 m2 per 20 ft; 1,585 kg gross per crate. Heat-treated ISPM 15 timber crates, 1180 x 820 mm footprint, faces separated with 2 mm closed-cell foam, EPS corner blocks, two-direction 19 mm steel banding.

SUPPLY

Trade supply by the container. Quotations to your nearest port or delivered to your yard, on request. Production 21 to 28 days, 24 to 32 days on the water. Batch test certificates issued with each shipment.

Mallikarjuna Stones Ltd, company no. 17314931, Suite 4 Cutlers Wharf, 18 Effingham Road, Sheffield S4 7YR. +44 114 496 0182, trade@mallikarjunastones.co.uk. Quarry and polishing yard: Mallikarjun Stone Polishing Industries, Survey No. 118/2 Hitnal Road, Miriyan Village, Chincholi Taluk, Kalaburagi District, Karnataka 585307.